

## ALSAN RS 210 resin

### Properties

ALSAN RS 210 Resin is a flexibilised methyl methacrylate-based resin formulation.

### Areas of application

ALSAN RS 210 Resin is used as a binder for the flexible self-levelling mortar ALSAN RS 233 used in the ALSAN RS Thick-Layer System.

### Colours

ALSAN RS 210 Resin is available in the following standard colours:

Shade 7032 – Pebble grey

Other colours are available on request.

### Packaging

Summer formulation

10.00 kg	ALSAN RS 210 Resin
<u>0.20 kg</u>	Catalyst (2 x 0.1 kg)
10.20 kg	

Winter formulation

10.00 kg	ALSAN RS 210 Resin
<u>0.40 kg</u>	Catalyst (4 x 0.1 kg)
10.40 kg	

### Storage

Can be stored unopened in a cool, dry place and protected against frost for approx. 6 months. Avoid direct sunlight on the packaging/containers, even on site.

### Application conditions

The product can be applied at substrate and ambient temperatures between + 3 ° min. and + 35 ° max.

### Mixing instructions

Stir the contents of the tub thoroughly, then add the catalyst while stirring at slow speed and mix for 2 minutes. Ensure that the material on the base and sides is mixed in.

### Reaction times (at 20 °C)

Pot life	approx. 15 minutes
Rain-proof after	approx. 30 minutes
Can be walked on / next layer can be applied after	approx. 1 hour
Fully cured after	approx. 3 hours

### Consumption

As binder in self-levelling mortar  
approx. 0.70 kg/m<sup>2</sup> mm

### Cleaning the tools

When work is interrupted or completed the tools must be cleaned thoroughly with ALSAN RS Cleaning Agent within the pot life (approx. 15 minutes) of the product.

### Information on risks and safety

See product safety data sheets.

The advice we provide on the application of our products is based on extensive development work as well as many years of experience and is given to the best of our knowledge. However, the wide variety of requirements for a building under the most diverse conditions mean that it is necessary for the contractor to test the product for its suitability in any given case. We reserve the right to make changes in keeping with technical developments or improvements to our products.

Version 0901