

ALSAN RS 273 TPO/FPO - primer

Properties

Alsan 273 TPO/FPO - Primer is a solvent free 1 component polyurethane based primer.

Areas of application

Alsan 273 TPO/FPO - Primer is used as primer for subsequent ALSAN waterproofing Systems.

Inappropriate

All other liquid systems

Substrates

All Soprema –Flag TPO/FPO membranes

Packaging

0, 8 kg metal can, colourless

Storage

Can be stored unopened in a cool, dry place and protected against frost for approx. 6 months. Avoid direct sunlight on the packaging/containers, even on site. Close the bottle immediately after use. Once the bottle is opened, the primer has a limited storage life and thickens to a gel after a short time, this product can then no longer be used.

Application conditions

The product can be applied at substrate and ambient temperatures between + 3 ° min. and + 35 ° max.

Substrate preparation

Clean substrate with Alsan cleaner and let it dry for 15 min. afterwards roughen up the substrate with appropriate tools.

Application

Stir the contents of the tub well before use. Put a thin layer of the primer using a brush. Be aware to avoid surcharges of primer in corner areas.

Reaction times (at 20 °C)

30°C	min 1 hour, max. 2 h.
20°C	min 1, 5 hours, max. 3 h.
10°C	min 2 hours, max. 4 h.
3°C	min 3 hour, max. 6 h.

Consumption

30–50 gr/m²

Cleaning the tools

When work is interrupted or completed the tools must be cleaned thoroughly with ALSAN RS Cleaning Agent.

Information on risks and safety

See product safety data sheets.

The advice we provide on the application of our products is based on extensive development work as well as many years of experience and is given to the best of our knowledge. However, the wide variety of requirements for a building under the most diverse conditions means that it is necessary for the contractor to test the product for its suitability in any given case. We reserve the right to make changes in keeping with technical developments or improvements to our products.

Version 0901