

ALSAN RS 288 Finish

Properties

ALSAN RS 288 Finish is a UV-stabilised, flexibilised and pigmented methyl-methacrylate-based resin formulation.

Areas of application

ALSAN RS 288 Finish is used as a sealer on the flexible, untopped version of the ALSAN RS Thick-Layer System using ALSAN RS 233 Self-Levelling Mortar.

Colours

ALSAN RS 288 Finish is available in the following standard colours:

Shade 7030 – Stone grey
Shade 7032 – Pebble grey
Shade 7043 – Traffic grey
Shade 1001 – Beige

:

Packaging

Summer formulation

10.00 kg	ALSAN RS 288 Finish
<u>0.20 kg</u>	<u>Catalyst (2 x 0.1 kg)</u>
10.20 kg	

Winter formulation

10.00 kg	ALSAN RS 288 Finish
<u>0.40 kg</u>	<u>Catalyst (4 x 0.1 kg)</u>
10.40 kg	

Storage

Can be stored unopened in a cool, dry place and protected against frost for approx. 6 months. Avoid direct sunlight on the packaging/containers, even on site.

Application conditions

The product can be applied at substrate and ambient temperatures between + 3 ° min. and + 35 ° max.

Mixing instructions

First stir the contents of the tub thoroughly, then add the catalyst while stirring at slow speed and mix for 2 minutes. Ensure that the material on the base and sides is mixed in.

Reaction times (at 20 °C)

Pot life	approx. 15 minutes
Rain-proof after	approx. 30 minutes
Can be walked on / next layer can be applied after	approx. 1 hours
Fully cured after	approx. 3 hours

Consumption

On even surfaces approx. 0.60 kg/m²

Cleaning the tools

When work is interrupted or completed the tools must be cleaned thoroughly with ALSAN RS Cleaning Agent within the pot life (approx. 15 minutes) of the product.

Information on risks and safety

See product safety data sheets.

The advice we provide on the application of our products is based on extensive development work as well as many years of experience and is given to the best of our knowledge. However, the wide variety of requirements for a building under the most diverse conditions mean that it is necessary for the contractor to test the product for its suitability in any given case. We reserve the right to make changes in keeping with technical developments or improvements to our products.

Version 0901