PRODUCT INFORMATION



ALSAN RS 222 Primer

Properties

ALSAN RS 276 Primer is a highly reactive, unpigmented methyl methacrylate-based resin formulation.

Areas of application

ALSAN RS 222 Primer is used for the pretreatment (as primer and barrier) of asphalt substrates for subsequent ALSAN RS Coating Systems in interior and exterior applications.

Colours

ALSAN RS 222 Primer is unpigmented.

Packaging

Summer formulation			
10.00 kg	ALSAN RS 222 Prim <mark>er</mark>		
0.30 kg	Catalyst (3 x 0.1 kg)		
10.30 kg			

Winter formulation

10.00 kg	ALSAN RS 222 Primer
0.60 kg	<u>Catalyst (6 x 0.1 kg)</u>
10.60 kg	

Storage

Can be stored unopened in a cool, dry place and protected against frost for approx. 6 months. Avoid direct sunlight on the packaging/containers, even on site.

Application conditions

The product can be applied at substrate and ambient temperatures between + 3 $^{\circ}$ min. and + 35 $^{\circ}$ max.

Catalyst dosage (on a 10 kg basis)

3 – 10 °C	0.6 kg
10 – 20 °C	0.4 kg
20 – 35 °C	0.2 kg

Mixing instructions

Stir the contents of the tub thoroughly, then add the catalyst while stirring at slow speed and mix for 2 minutes. Ensure that the material on the base and sides is mixed in.

Reaction times (at 20 °C)

Pot life	approx. 10 minutes	
Rain-proof after	approx. 30 minutes	
Can be walked on /		
next layer can be applied after		
	approx. 30 minutes	
Fully cured after	approx. 3 hours	

Consumption

On smooth substrates approx. 0.40 kg/m² On finely grained substrates approx. 0.50 kg/m² On rough substrates approx. 0.80 kg/m²

Cleaning the tools

When work is interrupted or completed the tools must be cleaned thoroughly with ALSAN RS Cleaning Agent within the pot life (approx. 10 minutes) of the product.

Information on risks and safety

See product safety data sheets.

The advice we provide on the application of our products is based on extensive development work as well as many years of experience and is given to the best of our knowledge. However, the wide variety of requirements for a building under the most diverse conditions mean that it is necessary for the contractor to test the product for its suitability in any given case. We reserve the right to make changes in keeping with technical developments or improvements to our products.

Version 0901