

# ALSAN MASTIC 2200

**Alsan Mastic 2200** is a non-cross-linkable sealant based on synthetic rubber plasticized with bitumen.

**Alsan Mastic 2200** is used in addition to bituminous waterproofing as grouting putty, caulking and filling joints. It is compatible with bituminous products (waterproofing membrane, shingles, ...).

**Alsan Mastic 2200** is used exclusively outdoors.

## Technical data and Properties

Technical Data		
<b>Chemical Base</b>	Synthetic rubber plasticized with bitumen	
<b>Curing system</b>	None	
<b>Density</b>	~1.1 kg/l	ISO 2811-1
<b>Flash point</b>	27°C	ASTMD56
<b>Cone penetrability</b>	175 ±25 1/10mm	NF T60-119
<b>Sag Flow</b>	0 mm	ISO 7390
<b>Service Temperature</b>	-20°C to +80°C	
<b>Application Temperature</b>	+5°C to +35°C	

## Instructions

Before application, be sure that surfaces are clean, dry, homogeneous and free from all contamination (oils and grease, dust and loose or friable particles). Cement laitance must be removed. **Alsan Mastic 2200** can be applied on slightly damp surfaces.

Apply **Alsan Mastic 2200** evenly. Extrude **Alsan Mastic 2200** into the joint to fill making sure that it is full contact with the side of the joint. Avoid air entrapment. Tool firmly against joint sides to ensure good adhesion.

Setting time is between 4 and 24 hours depending on the external conditions and the width of the joint dimensions.

The 310 ml cartridges are used with a standard cartridge extruder.

## Packaging

Packaging	Color(s)	Box
<b>Cartridge (CT)</b> 310 ml	Black	20 CT310

## Shelf-Life and Storage Conditions

---

12 months from date of production if stored in undamaged original and unopened packaging  
Store in dry conditions and protected from direct sunlight at temperatures between +10°C and +25°C.

## Ecology, Health and Safety Information (REACH)

---

For information and advice on the safe handling, storage and disposal of the chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety related data.

## Legal note

---

The information, and, in particular the recommendations relating to the application, contained in this Product Data Sheet is provided in good faith based on Soprema's current knowledge and experience of the product. It is deemed accurate at the date of publication of this document. Notwithstanding any intended uses specified in this document, due to differing conditions of use, the user remains liable to ensure the Product is suitable for its intended uses and applications and is legally compliant for the same. Therefore, Soprema gives no warranty, express or implied, regarding the fitness of the Product for any particular purpose. This information should not be construed as legal advice. Sales of the Product remain subject to the applicable terms and conditions of sale. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.