

## GEOTEXTILE 200

### Description

**GEOTEXTILE 200** is a non woven polyester fleece.

### Characteristics

Composition	Standard	Unit	Value	Tolerance
Composition			non woven polyester	
Mass		g/m <sup>2</sup>	200	
<b>Technical characteristics</b>				
Membrane thickness at 2 kPa	EN 9863-1	mm	1,7	± 15 %
Tensile force L	EN 10319	N/m	2760	± 15 %
Tensile force T	EN 10319	N/m	3800	± 15 %
Elongation at rupture L	EN 10319	%	35	± 15 %
Elongation at rupture T	EN 10319	%	45	± 15 %
Resistance to static puncture	EN 12236	N	600	-10/+0 %
Resistance to impact	EN 13433	mm	35	-0/+20 %
<b>Packing</b>				
Dimensions of the roll		m	100 x 2,2	
Mass of the roll		kg	± 44	

NPD = no performance determined

**GEOTEXTILE 200** is rot and bitumen resistant and has a high resistance against bacterial deterioration.

Store in a horizontal position in a dry place, protected against moisture and sunlight.

### Installation

**GEOTEXTILE 200** can be used as a compression-, separation- or protection layer on most supports.

To prevent deterioration it needs to be completely covered after installation (It can't be applied when permanently exposed to UV radiation).

### Special indications

#### Hygiene, Health and Environment

The product does not contain any substance which is likely to be detrimental to your health or to the environment and complies with generally admitted Health and Safety Requirements.

#### Quality-, Environment- and Safety Management

**SOPREMA** always recognises as a high level of importance the quality of the products, the environment and safety.

For this reason, we operate independently monitored Quality and Environment Assurance Systems in line with

**EN ISO 9001** and **EN ISO 14001**.