

EUROSTAR

WPBIT0050.b

DESCRIPTION	<p>EUROSTAR is a plastomeric modified bitumen waterproofing membrane (APP), industrially manufactured by impregnation of the reinforcement with the waterproofing compound based on distilled bitumen modified with polyolefin polymers of the latest generation, which gives to the compound superior technical characteristics.</p> <p>The composite reinforcement, made of nonwoven spunbond polyester in combination with fiberglass, conveys high mechanical characteristics, excellent dimensional stability, isotropic behaviour and elastic performance. Shaping of sheets, straightness, dimensional and surface uniformity are accomplished by hot calendaring of the mass at hot melt fluid state.</p> <p>It is a self-protected membrane. The upper surface can be completely coated with fine slate chips in "Black Diamond" version or coated with coloured slate chips and a selvage free at one side for easy welding overlap in mineral version.</p> <p>The lower surface is coated with a thermo-fusible polyolefin film.</p>
FIELD OF APPLICATION	<p>EUROSTAR is a top performance membrane and well above the other waterproofing membranes available on the market. It is particularly suitable as single layer and as top layer in multi-layer waterproofing systems, with compatible membranes, where required fire resistance (product class: B-roof (t2) in accordance with CEN TS 1187 and EN 13501-5).</p> <p>General roofing, vehicles parking roofs, foundations, on under floors or ground slabs, wall constructions, water tanks, tunnels, as protection from acid and basic solutions are valid examples of the design application of this product. It is not suitable for roof gardens. It can be applied onto every substrate (concrete, masonry, steel, wood, insulation panel, membrane, etc.) and under heavy protection or as underlayers for discontinuous roofing.</p> <p>The excellent mechanical characteristics and high level thermo-dynamic stability make it suitable for any climate conditions and all the situations where a barrier against water is required.</p>
METHOD OF INSTALLATION	<p>The excellent thermoplastic properties of the waterproofing compound allow the application with torch-on system or hot air generator. In particular situations, it could be applied with appropriate sealants or mechanical fastenings.</p> <p>The application of the membrane must be carried in good weather conditions and after the substrate has been adequately cleaned and prepared.</p>
PACKING AND STORAGE	<p>The product is packed as standing rolls on wooden pallets wrapped with thermoshrinking protective hoods. Rolls must be stored in the upright position, without stacking the pallets to avoid deformations which can compromise the correct application of the membrane. The product must be stored indoor, protected from heat and frost.</p>
INTENDED USE OR USES	<p>Flexible sheets for waterproofing. Reinforced bitumen sheets for roof waterproofing</p> <p>Flexible sheets for waterproofing. Bitumen damp proof sheets including bitumen basement tanking sheets</p> <p>Flexible sheets for waterproofing. Underlays for discontinuous roofing</p>

1. Mineral protection
2. Waterproofing mass
3. Reinforcement
4. Waterproofing mass
5. Torch-off film



EUROSTAR

WPBIT0050.b

TECHNICAL DATA


	Norm	Value		Unit	Tolerance
		4	5		
Thickness	EN1849-1	4	5	(mm)	±0,2
Roll length	EN1848-1	7,5	7,5	(m)	-1%
Roll width	EN1848-1	1,1	1,1	(m)	-1%
Straightness	EN1848-1	PASSED		-	20 mm / 10 m
Flexibility at low temperature (pliability)	EN1109	-30		(°C)	≤
Heat flow resistance	EN1110	140		(°C)	≥
Watertightness	EN1928-B	60		(kPa)	≥
Watertightness	EN1928-A W1	PASSED		(kPa)	2kPa/2h
Water vapour transmission properties	EN1931	20.000		(μ)	-
		M.d. C.d.			
Tensile properties: maximum tensile strength	EN12311-1	850 / 750		(N/50 mm)	-20%
Tensile properties: elongation at break	EN12311-1	40 / 40		(%)	-15
Resistance to tearing (nail shank)	EN12310-1	250 / 250		(N)	-30%
Dimensional stability	EN1107-1	±0,2 / ±0,2		(%)	≤
Peal resistance of joints	EN12316-1	50 / 50		(N/50 mm)	-20
Shear resistance of joints	EN12317-1	850 / 750		(N/50 mm)	-20%
Resistance to static puncture	EN12730-A	20		(kg)	≥
Resistance to impact	EN12691-A	1250		(mm)	≥
External fire performance (note 1)	EN1187/EN13501-5+A1	Broof t2 *		Class	-
Reaction to fire	EN11925-2/EN13501-1+A1	E		Class	-
Root resistance	EN13948	NPD			
Determination of adhesion of granules (Loss)	EN12039	PASSED		(%)	<30
Visible defects	EN1850-1	PASSED		-	-
Durability: Flexibility at low temperature after artificial ageing	EN1296/EN1109	-30		(°C)	+15
Durability: Flow resistance at elevated temperature after artificial ageing	EN1296/EN1110	130		(°C)	-10
Durability: Watertightness after artificial ageing	EN1296/EN1928-B	PASSED		(kPa)	≥ 60
Durability: Visual defects after artificial ageing	EN1297/EN1850-1	PASSED		-	PASSED
Durability: Watertightness against chemicals	EN1296/EN1847	NPD			
Artificial ageing by long term exposure to the combination of UV radiation and elevated temperature and heat: Tensile strength	EN1296/EN12311-1	NPD			
Artificial ageing by long term exposure to the combination of UV radiation and elevated temperature and heat: Elongation	EN1296/EN12311-1	NPD			
Artificial ageing by long term exposure to the combination of UV radiation and elevated temperature and heat: Watertightness	EN1296/EN1928-A	W1		Class	-

WARNINGS


* Classification valid only for the application of the membrane for systems as indicated by certification available on request.

NORMS

EN13707; EN13969; EN13859-1



Single layer on bituminous glue



Top layer in multi-layer systems



Fire Resistance




Under layers for discontinuous roofing




Damp proof courses



Foundations



Car park roofs



Multilayer systems under heavy protection