

SOPRALENE FLAM VENTI 180 AF

Description

Membrane with a vapour-pressure and tension dispersion system, composed of SBS modified bitumen and a non woven polyester reinforcement.

Used as single layer waterproofing on surfaces where partial adhesion are required.

The upper surface is finished with slates and the overlap is protected by a thermofusible film.

The lower surface is provided with thermofusible bitumen stripes alternated with non-stick stripes protected by a thermofusible film.

Composition

	SOPRALENE FLAM VENTI 180 AF
Reinforcement	non woven polyester
Finishing upper side	slates
Colour	natural black
Finishing lower side	thermofusible film
Coating mass	SBS modified bitumen

Packing

	SOPRALENE FLAM VENTI 180 AF
Dimensions of the roll (m)	6 x 1
Mass/roll (kg)	36
Rolls/pallet	25

Characteristics

		SOPRALENE FLAM VENTI 180 AF
Membrane thickness (mm) (EN 1849-1)	MDV	4,5
Tensile force L (N/5cm) (EN 12311-1)	MDV	850
Tensile force T (N/5cm) (EN 12311-1)	MDV	650
Elongation at maximum tensile force L (%) (EN 12311-1)	MDV	45
Elongation at maximum tensile force T (%) (EN 12311-1)	MDV	45
Dimensional stability (%) (EN 1107-1)	MLV	0,5
Resistance to tearing (nail shank) L (N) (EN 12310-1)	MDV	175
Resistance to tearing (nail shank) T (N) (EN 12310-1)	MDV	175
Flexibility at low temperature (°C) (EN 1109)	MLV	-20
Flow resistance at elevated temperature (°C) (EN 1110)	MLV	110

MDV = manufacturer declared value / MLV = manufacturer limiting value / NPD = no performance determined

Installation

- Torch-on or hot-air method including the overlaps.

SOPREMA reserves the right to amend the composition of its material and consequently their prices, without prior notice. For this reason, all orders will be accepted only in accordance with the conditions and technical specifications in force at the date of order.

**SOPREMA**

Bituminous waterproofing

TECHNICAL DATASHEET



BETF-WPBBE0347.a/EN
cancels and replaces
BETF-347/043-14/EN

Certifications



No.: **0749**
Standard: **EN 13707**
Year: **2014**

Special indications

Hygiene, Health and Environment

The membrane does not contain any substance which is likely to be detrimental to your health or to the environment and complies with generally admitted Health and Safety Requirements.
For more information, please refer to the relevant safety data sheet.

Quality-, Environment- and Safety Management

SOPREMA always recognises as a high level of importance the quality of the products, the environment and safety.

For this reason, we operate independently monitored Quality and Environment Assurance Systems in line with **EN ISO 9001** and **EN ISO 14001**.



Marnix DERKS
Technical Director
Grobbendonk, 17/10/2017

SOPREMA reserves the right to amend the composition of its material and consequently their prices, without prior notice. For this reason, all orders will be accepted only in accordance with the conditions and technical specifications in force at the date of order.

United Kingdom:
SOPREMA UK Limited
T: +44 (0)8451 948 727
F: +44 (0)8451 948 728
E: info@soprema.co.uk
W: www.soprema.co.uk

Ireland:
SOPREMA Limited
T: +353 (0)1 405 7796
F: +353 (0)1 462 5887
E: info@soprema.ie
W: www.soprema.ie

SOPREMA
GROUP