

STRATOS R6

COLD ASPHALT REPAIR

USE

STRATOS R6 is a cold asphalt mix with polymers modified bitumen.

The cold application allows an easy and fast treatment for new build applications (parking decks, driveways ...) and refurbishment such as potholes.

Once repaired, the surface presents the same characteristics than the rest of the asphalted area. The product will reach the required resistance after 10 to 20 days of its application, depending on the weather conditions.



APPLICATION

The surface must be dry and clean (no grease, no oil, no non-cohesive elements).

STRATOS R6 is placed in excess on the area to be treated then tamped. Once the repair works completed, it must be levelled.

For an immediate traffic circulation, sand dust must be applied

STRATOS R6 can be applied in successive layers up to 5 cm, without exceeding a total thickness of 10 cm.

STRATOS R6 has to be preferably used at a temperature above +10° C.

DESCRIPTION

STRATOS R6 is cold applied thanks to its composition made of gravels embedded in a bitumen modified with polymers. A disposable liner bag allows reuse of the can and a traditional waste treatment.

One 25 kg bucket allows to cover a 1 m² area with an approximately 10 mm thick product.

CIVILROCK prides itself in working with the highest quality products. We operate with quality assurance systems, and are certified ISO 9001.

✓ Easy and quick to install

✓ Cold applied

✓ Immediate traffic circulation

CHARACTERISTICS

ESSENTIAL CHARACTERISTICS	Standard	STRATOS R6
Physical state		Black solid
Density before compaction (kg/dm ³)		1,6 to 1,8
Density after compaction (kg/dm ³)		2,3 to 2,5
Grain size		0/4
Type of aggregates		Limestone

PACKAGING

Can (kg)	25
----------	----

MARKING

Unique identification code of the product type : MISES0162.