

SOPRALENE FLAM UNILAY

SOPRALENE FLAM UNILAY is a SBS elastomeric bitumen waterproofing membrane with a non-woven polyester reinforcement.

Both sides are protected by a thermofusible film.

User application

SOPRALENE FLAM UNILAY is used as unilayer under gravel or slabs on pads, or backfilling in association with an anti-root membrane (buried works) or as first or second layer under protection in all two-ply elastomeric bitumen waterproofing systems. To be used outside only.

All the applications are described in Technical Approvals or **SOPREMA**'s Technical Guidelines in force.

Composition

		SOPRALENE FLAM UNILAY
Reinforcement		Non-woven polyester
Binder		Elastomeric bitumen: blend of selected bitumen and SBS* thermoplastic polymers
Thickness	On overlap	4,0 mm (-5 % ; + 5 %)
Topside		Thermofusible film
Underside		Thermofusible film
Overlap		≥ 100 mm
*According to UEAtc directives concerning the normalization of waterproof elastomeric SBS bitumen coverings		

Packaging

		SOPRALENE FLAM UNILAY
Dimensions of the roll		8 m x 1 m
Weight of the roll		about 39 kg
Storage		Upright on pallet with plastic wrapping
<p>Roll lengths are given with a tolerance of $\leq 1\%$. Roll can be cut in two parts. In this case, the shortest length is 2 meters and the total length is equal to the nominal length.</p> <p>Width of roll is given with a tolerance of 1% (UEAtc). Rolls must be stored upright on flat ground. Pallets may be stacked to a maximum of two high with separating layer. During storage, protect the rolls against moisture. In cold weather, we recommend that the rolls be kept at a minimum temperature of + 2°C (+ 36 °F) for at least 5 hours before installation.</p>		

Characteristics (off CE marking)

	SOPRALENE FLAM UNILAY
Static puncture resistance (NF P 84-352)	≥ 25 kg (L4)
Dynamic puncture resistance (NF P 84-353)	≥ 20 J (D3)
FIT classification when used as monolayer	F5 I5 T4

Installation

SOPRALENE FLAM UNILAY must be applied only by heat welding or torch-on techniques.

Hot bitumen must not be used in the bonding process.

Special indications

Hygiene, health and environment:

The product does not contain any substance likely to be detrimental to health or to environment and complies with generally admitted Health and Safety Requirements. For further information, please refer to relevant Safety Data Sheet.

Traceability:

Product traceability is ensured through a manufacturing code present on the packaging.

Quality control:

SOPREMA has always attached the highest importance to the quality of its products, to the respect of environment and men.

For this reason, we apply an integrated management of the Quality and Environment certified **ISO 9001** and **ISO 14001**.

CE marking

 1119
SOPRALENE FLAM UNILAY SOPREMA 14 rue de Saint-Nazaire – CS 60121 67025 STRASBOURG cedex 06 Construction Product Regulation (CPR) Declaration of Performance : DoP n° WPBFR237 Certificate of Factory Production Control : 2007-CPR-13132, 13133, 13134 (EN 13707). Certificate of Factory Production Control : 2007-CPR-13136, 13137, 13138 (EN 13969).
EN 13707 / EN 13969 Membrane composed of modified elastomeric bitumen and non-woven polyester reinforcement. Both sides are protected by a thermofusible film. Dimensions : 8 m x 1 m x 4,0 mm. Applied by torch-on techniques. Unilayer, first or second layer under protection.

Essential characteristics	Performances	Harmonised Technical Specification
Classification for external fire exposure (Note 1)	F_{ROOF} (t1,t2,t3,t4)	EN 13707:2004 + A2:2009
Root resistance	NPD	
Peel resistance of joints (N / 50 mm)	≥ 100	
Durability Flow resistance at elevated temperature after ageing	90°C	EN 13969:2004
Durability Watertightness after ageing	Conform	
Resistance to static loading – Method B (kg)	15	EN 13707:2004 + A2:2009 EN 13969:2004
Reaction to fire	E	
Watertightness	Conform	
Resistance to impact – Method A (mm)	1750	
Shear resistance of joints (N / 50 mm)	≥ 800	
Flexibility at low temperature	-16°C	
Tensile properties : Tensile strength L x T (N / 50 mm) Elongation L x T (%)	≥ 800 x 800 40 x 40	
Resistance to static loading – Method A (kg)	20	
Resistance to tearing (N)	≥ 250	
Dangerous substances (Notes 2 and 3)	Complies	

Note 1 : Since external fire performance depends on the other components of the roof build-up, no performance can be given.

Note 2 : This product does not contain asbestos or tar constituents.

Note 3 : Since there is no European test method available, no performance declaration for leaching behavior can be made. It must be made according to national rules in force in the place of use.

Additional characteristics	SOPRALENE FLAM UNILAY
	MLV*
Flow resistance at elevated temperature (EN 1110)	100 °C
Dimensional stability (EN 1107-1)	0,5 %
*MLV = Manufacturer's Limiting Value: Minimum value as started by the manufacturer to be met during testing of type, internal quality control or external supervision with a confidence level of 95 %	