

Technical Data Sheet N° WPSIT0055.b
 Cancels and replaces WPSIT0055.a

DESCRIPTION

Synthetic membrane of plasticized PVC obtained by cast process, reinforced with a polyester mesh and coupled on the back sheet with a non-woven geotextile of 200 g/m².
 Manufactured in a plant certified UNI EN ISO 9001 (Quality management system) and UNI EN ISO 14001 (environmental management system).
 Setting performed by applicators approved by Soprema srl.
 Finishing and accessories composed by elements produced and approved by Soprema srl.

FEATURES

- Resistant to wind stress
- High resistance to weathering and UV rays
- High mechanical resistance
- Resistant to puncturing
- RAL colouring available on request for landscape or architectural purposes

AREA OF USE

ROOFING

- Exposed roof, with mechanical fastening system
- Mixed solution: mechanical fastening system + fully adhered system

PROPERTIES

		SRF 1,20	SRF 1,50	SRF 1,80	SRF 2,00	Test method
Thickness	(mm)	1,20	1,50	1,80	2,00	EN 1849-2
Weight	(kg/m ²)	1,70	2,00	2,35	2,60	EN 1849-2
Tensile strength	(N/5cm)	≥ 1100	≥ 1100	≥ 1100	≥ 1100	EN 12311-2
Elongation to break	(%)	≥ 15	≥ 15	≥ 15	≥ 15	EN 12311-2
Tear resistance	(N)	≥ 200	≥ 200	≥ 200	≥ 200	EN 12310-2
Impact resistance on rigid support	(mm)	≥ 450	≥ 800	≥ 900	≥ 1250	EN 12691
Cold bending	(°C)	≤ - 25	≤ - 25	≤ - 25	≤ - 25	EN 495-5
Hydrostatic pressure resistance (6 hours at 0,5 Mpa)		waterproof	waterproof	waterproof	waterproof	EN 1928 met. B
Dimensional stability (6 hours at 80°C)	(%)	≤ 0,5	≤ 0,5	≤ 0,5	≤ 0,5	EN 1107-2
Resistance against artificial weathering	(UV)	no surface cracking	no surface cracking	no surface cracking	no surface cracking	EN 1297
Resistance to roots penetration		no penetration	no penetration	no penetration	no penetration	EN 13948
Resistance to static punching	(kg)	≥ 20	≥ 20	≥ 20	≥ 20	EN 12730
Fire resistance		E	E	E	E	EN ISO 11925-2 EN 13501-1

PRODUCTION STANDARD

Thickness	1,20 mm	1,50 mm	1,80 mm	2,00 mm	
Width	1,65 m	1,65 m	1,65 m	1,65 m	
Number of rolls on each pallet	16	16	12	12	
Length	20 m	20 m	20 m	20 m	
Colour (surface / underside)	LIGHT GREY / TNT				

CE MARKING

Unique identification code of the product-type: WPSIT0055

FLAGON SRF membranes are produced by the company SOPREMA srl in Villa Santo Stefano are CE marked no.1085-CPR-018 in accordance with EN 13956:2012.

Due to its formulation, the liner is NOT subject to the requirements set forth in the CLP Regulation (EC) No 1272/2008 and EU n° 487/2013 and subsequent amendments on dangerous substances. If the product should be disposed of as a waste, we recommend sending it to an authorised landfill site or to an incinerator equipped with post-combustion chamber and fumes washing system.
 The data herewith indicated, apart from those required by EC branding, are not exhaustive and SOPREMA srl may modify them without previous notice. SOPREMA srl, has the right to modify the product at any time and without previous notice, in any of its aspect, and to stop its production.
 SOPREMA srl reserves the right, as technology and know-how progress, to modify without warning the composition and conditions of use of its materials, and subsequently their price. As a result, orders shall only be accepted on the basis of the terms and technical specifications applicable at the time of receipt.