

# ALSAN PATCH

## 1 PRESENTATION

**ALSAN PATCH** is a solvent based waterproofing paste composed of high polymers for temporary local repair purposes.

## 2 CHARACTERISTICS

	<b>ALSAN PATCH</b>
<b>Aspect</b>	Viscous liquid Turns grey and rubbery once dry
<b>Density at 20°C (ASTM D1475)</b>	± 1030 kg/m <sup>3</sup>
<b>Thickness</b>	about 1000 µm wet, about 430 µm dry
<b>Solid content (ASTM D1644/a)</b>	51-54 % of weight / 42-44 % of volume
<b>Flash point (DIN 53 213)</b>	> 23°C, flammable
<b>Re-covering time</b>	After 3 to 14 days
<b>Classification (AFNOR NF T 36-005)</b>	Family I, Class 7b1

## 3 PACKAGING AND CONSUMPTION

Cans: 1 liter or 5 liters.

Consumption: 1 to 2,5 liters/m<sup>2</sup>

Storage: at least 5 years in a cool, unopened container turned upside-down, away from any source of heat, with a temperature between +5°C and +35°C.

## 4 USER'S APPLICATION

**ALSAN PATCH** is used as temporary local repairing for roofs, terraces, cornices, gutters, chimneys, pipes...

Immediate repairing; up to 1300% elasticity; excellent resistance to the elements; mineral acids (max 10% concentration); does not contain any bitumen substances, excellent hold on various surfaces.



## 5 INSTALLATION

- Installation conditions: **ALSAN PATCH** can also be applied in humid weather. To be applied on a clean surface.
- Particularity: Product must never be applied onto polystyrene insulation.
- Spatula, brush and roller: do not dilute.
- Tool cleaning: **Diluant V** (thinner).

## 6 SPECIAL INDICATIONS

### Hygiene, health and environment:

- Flammable: ensure that all cans, empty or full, of flammable substances are at least 10 m away.
- Do not breathe vapour.
- Avoid skin contact.
- Keep product away from any flames or sparks – do not smoke.
- Only use in well-ventilated areas.

For more information, please refer to the relevant Safety Data Sheet.

### Quality control:

**SOPREMA** has always attached the highest importance to Quality Control. For this reason, we operate an internationally recognized Quality System according to **ISO 9001: 2008** with the system being independently monitored and certified by **BSI**.

