

FLAGON EP/PR SC

Technical Data Sheet N° WPSIT0096.b

Cancels and replaces WPSIT0096.a

COMPOSITION

Synthetic membrane manufactured in TPO modified polyolefin, double colour sand-grey/black, obtained by co-extrusion, reinforced by a polyester mesh.

The upper sand grey layer is featured by a very high resistance to weather and UV rays, while the underlying black layer is punching resistant.

Manufactured in a plant certified by UNI EN ISO 9001 (Quality management system) and UNI EN ISO 14001 (environmental management system).

Laying performed by technicians approved by Soprema srl.

Finishing and accessories composed by elements produced and approved by Soprema srl.

FEATURES

- Weatherproof and UV resistance
- Resistant to wind stress
- Mechanical resistance and resistance to punching
- Adaptability to structural movements
- Good flexibility at low temperatures
- Also available in the following RAL colors:
 - RAL 9016 (white/black), with solar reflectance index (SRI) 82, according to ASTM E 1980

AREAS OF USE

ROOFING

- Exposed roof, with mechanical fastening system

PROPERTIES

	EP/PR SC 1,50	EP/PR SC 1,80	EP/PR SC 2,00	Test method
Thickness (mm)	1,50	1,80	2,00	EN 1849-2
Weight (kg/m ²)	1,90	2,28	2,54	EN 1849-2
Tensile strength (N/5cm)	≥ 1100	≥ 1100	≥ 1100	EN 12311-2
Elongation to break (%)	≥ 15	≥ 15	≥ 15	EN 12311-2
Tear resistance (N)	≥ 300	≥ 300	≥ 300	EN 12310-2
Resistance to impact (mm)	≥ 800	≥ 900	≥ 1250	EN 12691
Cold bending (°C)	≤ - 25	≤ - 25	≤ - 25	EN 495-5
Hydrostatic pressure resistance (6 hours at 0,5 Mpa)	waterproof	waterproof	waterproof	EN 1928 met. B
Dimensional stability (%)	≤ 0,5	≤ 0,5	≤ 0,5	EN 1107-2
Resistance to artificial weathering (UV)	no surface cracking	no surface cracking	no surface cracking	EN 1297
Resistance to static punching (kg)	≥ 20	≥ 20	≥ 20	EN 12730
Fire behaviour* (class)	B roof t2 B roof t3	B roof t2 B roof t3	B roof t2 B roof t3	ENV 1187 e EN 13501-5
Fire resistance (class)	E	E	E	EN ISO 11925-2 e EN 13501-1

* classification valid only for the application of the membrane for systems as indicated by certification available on request.

PRODUCTION STANDARD

Thickness	1,50 mm		1,80 mm		2,00 mm		
Width	1,05 m	2,10 m	1,05 m	2,10 m	1,05 m	2,10 m	
Number of rolls on each pallet	23	14	18	14	18	36	
Length	20 m		20 m		20 m		
Colour (surface / underside) SAND GREY / BLACK							

CE MARKING

Unique identification code of the product-type: WPSIT0096

FLAGON EP/PR SC membranes are produced by the company SOPREMA srl in Chignolo d'Isola (Italy) and are CE marked no.1085-CPR-011 in accordance with EN 13956:2012.

Due to its formulation, the liner is NOT subject to the requirements set forth in the CLP Regulation (EC) No 1272/2008 and EU n° 487/2013 and subsequent amendments on dangerous substances. If the product should be disposed of as a waste, we recommend sending it to an authorised landfill site or to an incinerator equipped with post-combustion chamber and fumes washing system. The data herewith indicated, apart from those required by EC branding, are not exhaustive and SOPREMA srl may modify them without previous notice. SOPREMA srl, has the right to modify the product at any time and without previous notice, in any of its aspect, and to stop its production. SOPREMA srl reserves the right, as technology and know-how progress, to modify without warning the composition and conditions of use of its materials, and subsequently their price. As a result, orders shall only be accepted on the basis of the terms and technical specifications applicable at the time of receipt.