

FLAGON FLEXOCOL EP

Description

FLAGON FLEXOCOL EP is a ready-to-use, single component, synthetic rubber based, contact adhesive for non-backed TPO waterproofing membranes.

Characteristics

Composition	synthetic rubber
Open time ⁽¹⁾	±30 min. (20 °C)
Curing time ⁽¹⁾	±60 min. (20 °C)
Consumption	2-4 m ² /l
Application temperature	+5 / +25 °C

⁽¹⁾ Depending on conditions (temperature, relative humidity, ...)

Packing & storage

Can of 20 l

Minimum 12 months in original unopened packaging, stored in a dry and cool place at a temperature between +5 and +25 °C.

Installation

The substrate and the membrane must be clean, solid and free from dust and grease.

Use a lambs-wool roller to apply an even layer of adhesive on both surfaces.

As soon as the adhesive becomes tacky, but dry (5 to 30 minutes), roll the coated membrane onto the coated substrate.

Use a roller or by hand to press the membrane into the adhesive.

Prevent air entrapments.

Cleaning tools:

- remove uncured product with FLAGON Solvent 13
- cured product needs to be removed mechanically

Special indications

Hygiene, Health and Environment

For more information, please refer to the relevant safety data sheet.

Quality-, Environment- and Safety Management

SOPREMA always recognises as a high level of importance the quality of the products, the environment and safety.

For this reason, we operate independently monitored Quality and Environment Assurance Systems in line with

EN ISO 9001 and **EN ISO 14001**.