

TECHNICAL DATASHEET



BETF-WPBBE0406.b/EN cancels and replaces
BETF-WPBBE0406.a/EN

SOPRAROCK GLOBAL SBS 30 TF

Description _

Membrane composed of SBS modified bitumen and a composite polyester reinforcement.

Used as an under layer within a multi layer waterproofing system.

The upper surface is finished with talcum/sand.

The lower surface is protected by thermofusible film.

Composition ____

	SOPRAROCK GLOBAL SBS 30 TF	
Reinforcement	composite polyester	
Finish upper side	talcum/sand	
Finish lower side	thermofusible film	
Coating mass	SBS modified bitumen	

Packing

	SOPRAROCK GLOBAL SBS 30 TF
Dimensions of the roll (m)	10 x 1
Mass/roll (kg)	37
Rolls/pallet	30

Characteristics

		SOPRAROCK GLOBAL SBS 30 TF
Membrane thickness (mm) (EN 1849-1)	MDV	3,0
Membrane mass (kg) (EN 1849-1) (indicative)	MDV	3,7
Tensile force L (N/5cm) (EN 12311-1)	MDV	650
Tensile force T (N/5cm) (EN 12311-1)	MDV	450
Elongation at maximum tensile force L (%) (EN 12311-1)	MDV	35
Elongation at maximum tensile force T (%) (EN 12311-1)	MDV	35
Dimensional stability (%)(EN 1107-1)	MLV	0,3
Resistance to tearing (nail shank) L (N) (EN 12310-1)	MDV	125
Resistance to tearing (nail shank) T (N) (EN 12310-1)	MDV	125
Flexibility at low temperature (°C) (EN 1109)	MLV	-20
Flow resistance at elevated temperature (°C) (EN 1110)	MLV	110

 $\mathsf{MDV} = \mathsf{manufacturer} \ \mathsf{declared} \ \mathsf{value} \ \ / \ \ \mathsf{MLV} = \mathsf{manufacturer} \ \mathsf{limiting} \ \mathsf{value} \ \ / \ \ \mathsf{NPD} = \mathsf{no} \ \mathsf{performance} \ \mathsf{determined}$

SOPREMA reserves the right to amend the composition of its material and consequently their prices, without prior notice. For this reason, all orders will be accepted only in accordance with the conditions and technical specifications in force at the date of order.

Contact: www.Soprema.com





TECHNICAL DATASHEET



BETF-WPBBE0406.b/EN cancels and replaces
BETF-WPBBE0406.a/EN

Installation

- Torch-on or hot-air method including the overlaps.
- Mechanically fastened in the overlap, overlaps torched.

Certifications

((

No.: **0749**Standard: **EN 13707**Year: **2017**

FM approved



Special indications

Hygiene, Health and Environment

The membrane does not contain any substance which is likely to be detrimental to your health or to the environment and complies with generally admitted Health and Safety Requirements. For more information, please refer to the relevant safety data sheet.

Quality-, Environment- and Safety Management

SOPREMA always recognises as a high level of importance the quality of the products, the environment and safety.

For this reason, we operate independently monitored Quality and Environment Assurance Systems in line with **EN ISO 9001** and **EN ISO 14001**.



Marnix DERKS Technical Director

Grobbendonk, 29/01/2018

SOPREMA reserves the right to amend the composition of its material and consequently their prices, without prior notice. For this reason, all orders will be accepted only in accordance with the conditions and technical specifications in force at the date of order.

Contact: www.Soprema.com

