

MAMMOUTH SBS ALU FLAM PROVENCE

MAMMOUTH SBS ALU FLAM PROVENCE is flexible SBS elastomeric bitumen waterproofing membrane with a glass grid / glass fleece reinforcement.

The topside is protected by an embossed aluminium foil, thermostable and coloured (which harmonizes with the colour of the tiles) and the underside is covered by a thermofusible film.

User application

MAMMOUTH SBS ALU FLAM PROVENCE, with its adapted colour to the tiles one, can be used to create different roof works: for example, around chimneys and other penetrations, valleys. To be used outside only.

Composition

	MAMMOUTH SBS ALU FLAM PROVENCE
Reinforcement	Glass grid + glass fleece
Binder	Elastomeric bitumen : blend of selected bitumen and SBS* thermoplastic polymers
Thickness MDV ⁽¹⁾ according to 13707	3,5 mm (-0 % ; +10 %)
Topside	Coloured embossed aluminum foil - Thickness: 0,08 mm (-0,015 mm)
Underside	Thermofusible film
Overlap	≥ 60 mm
*According to UEAtc directives concerning the normalization of waterproof elastomeric SBS bitumen coverings (¹) MDV = Manufacturer's Declared Value	

Packaging

	MAMMOUTH SBS ALU FLAM PROVENCE
Dimensions of the roll	8 m x 1 m
Weight of the roll	about 32 kg
Storage	Upright on pallet with plastic wrapping
Roll lengths are given with a tolerance of ≤ 1 %. Roll can be cut in two parts. In this case, the shortest length is 2 meters and the total length is equal to the nominal length. Width of roll is given with a tolerance of 1% (UEAtc). Rolls must be stored upright on flat ground. Pallets may be stacked to a maximum of two high with separating layer. During storage, protect the rolls against moisture. In cold weather, we recommend that the rolls be kept at a minimum temperature of + 2°C (+ 36 °F) for at least 5 hours before installation.	

*Prevents from the arduousness for roofers on worksite

Characteristics (off CE marking)

MAMMOUTH SBS ALU FLAM PROVENCE characteristics are compliant with standard P84-316 (TV th type).

Installation

MAMMOUTH SBS ALU FLAM PROVENCE is applied only by torch-on techniques.
Hot bitumen must not be used in the bonding process.

Special indications

Hygiene, health and environment:

The product does not contain any substance likely to be detrimental to health or to environment and complies with generally admitted Health and Safety Requirements. For further information, please refer to relevant Safety Data Sheet.


Traceability:

Product traceability is ensured through a manufacturing code present on the packaging.

Quality control:

SOPREMA has always attached the highest importance to the quality of its products, to the respect of environment and men.
For this reason, we apply an integrated management of the Quality and Environment certified **ISO 9001** and **ISO 14001**.

CE marking

 2007		
MAMMOUTH SBS ALU FLAM PROVENCE SOPREMA 14 rue de Saint-Nazaire – CS 60121 67025 STRASBOURG cedex 06 Construction Product Regulation (CPR) Declaration of Performance : DoP n° WPBFR215 Certificate of Factory Production Control : 2007-CPR-13105, 13107, 13109.		
EN 13707 Membrane composed of modified elastomeric bitumen and a glass grid/glass fleece reinforcement. Topside is protected with an embossed metal foil and underside is covered by a thermofusible film. Dimensions : 8 m x 1 m x 3,5 mm. Applied by torch-on techniques.		

Essential characteristics	Performances	Harmonised Technical Specification
Classification for external fire exposure (Note 1)	F_{ROOF} (t1,t2,t3,t4)	EN 13707:2004 + A2:2009
Reaction to fire	E	
Watertightness	Conform	
Tensile properties : Tensile strength L x T (N / 50 mm) Elongation L x T (%)	≥ 600 x 600 2 x 2	
Root resistance	NPD	
Resistance to static loading (kg)	5	
Resistance to impact (mm)	1750	
Resistance to tearing (N)	≥ 150	
Joint strength Peel resistance of joints (N / 50 mm) Shear resistance of joints (N / 50 mm)	NPD NPD	
Durability Flow resistance at elevated temperature after ageing	70°C	
Flexibility at low temperature	-10°C	
Dangerous substances (Notes 2 and 3)	Complies	

Note 1 : Since external fire performance depends on the other components of the roof build-up, no performance can be given.

Note 2 : This product does not contain asbestos or tar constituents.

Note 3 : Since there is no European test method available, no performance declaration for leaching behavior can be made. It must be made according to national rules in force in the place of use.

Additional characteristics	MAMMOUTH SBS ALU FLAM PROVENCE
	MLV*
Flow resistance at elevated temperature (EN 1110)	80 °C
Dimensional stability (EN 1107-1)	0,5 %
*MLV = Manufacturer's Limiting Value: Minimum or maximum value as started by the manufacturer to be met during testing of type, internal quality control or external supervision with a confidence level of 95 %	