



TECHNICAL DATASHEET

BETF-MISFR0105.a/EN
cancels and replaces
BETF-10-03/20.1/EN

SOPRAVAP 3/1

Description

Is a 2-component liquid, polyurethane based resin which after drying and curing fulfills the 3 properties of primer, vapour barrier and glue.

It is used for bonding insulation boards with a suitable finish (EPS, PUR, PIR, mineral wool and perlite) on a concrete substrate.

Characteristics

	SOPRAVAP 3/1
Composition	polyurethane resins
Open time ⁽¹⁾	30 min. (20 °C)
Curing time ⁽¹⁾	2 h (20 °C)
Consumption (kg/m ²)	min. 2 (min. 1,5 mm after drying)
Application temperature	+5 / +35 °C
Water vapour diffusion-equivalent (m) (EN 1931)	125 (layer 1,5 mm after drying)

(1) Depending on conditions (temperature, relative humidity, ...)

Packing & storage

Kit 25 kg (A: 20,7 kg / B: 4,3 kg)

6 months in original unopened packaging (upside down for component B). Store cool, dry and frost-free at a temperature between +10 °C and +30 °C.

Installation

Add the whole of component B to component A.

Homogenize for at least 3 minutes with a suitable mixer (ex. paint mixer) in order to obtain a uniform mass.

Apply with a rubber or metallic toothed trowel or squeegee (teeth 7 mm).

The substrate must be dry, clean, solid and free from dust and grease.

Place the insulation boards with a light pressure onto the wet, uncured product.

Cleaning tools:

- wet product: White Spirit or DILUANT V



SOPREMA

Bituminous waterproofing

TECHNICAL DATASHEET

BETF-MISFR0105.a/EN
cancels and replaces
BETF-10-03/20.1/EN

Special indications

Hygiene, Health and Environment

The membrane does not contain any substance which is likely to be detrimental to your health or to the environment and complies with generally admitted Health and Safety Requirements.
For more information, please refer to the relevant safety data sheet.

Quality-, Environment- and Safety Management

SOPREMA always recognises as a high level of importance the quality of the products, the environment and safety.

For this reason, we operate independently monitored Quality and Environment Assurance Systems in line with **EN ISO 9001** and **EN ISO 14001**.



Marnix DERKS
Technical Director
Grobbendonk, 15/03/2018

SOPREMA reserves the right to amend the composition of its material and consequently their prices, without prior notice. For this reason, all orders will be accepted only in accordance with the conditions and technical specifications in force at the date of order.

Contact: www.Soprema.com

SOPREMA
GROUP