

## XPS SL

### Description

**XPS SL** is a rigid thermal insulation board made of extruded polystyrene (XPS) foam produced according to climate-friendly CO<sub>2</sub> technology.

**XPS SL** is mainly used as thermal insulation including flat and pitched roofs, floors and underground constructions. On flat roofs the system must be ballasted.

### Packing & Storage

Thickness (mm)	Boards/pack	m <sup>2</sup> /pack	Boards/pallet <sup>(1)</sup>	m <sup>2</sup> /pallet <sup>(1)</sup>	Thermal resistance (R <sub>0</sub> ) (m <sup>2</sup> .K/W)
30	14	10,50	168	126,0	0,90
40	10	7,50	120	90,0	1,20
50	8	6,00	96	72,0	1,50
60	7	5,25	84	63,0	1,80
80	5	3,75	60	45,0	2,25
100	4	3,00	48	36,0	2,85
120	3	2,25	42	31,5	3,40
140	3	2,25	36	27,0	4,00
160	2	1,50	32	24,0	4,55
180	2	1,50	28	21,0	5,10
200	2	1,50	24	18,0	5,70
220	2	1,50	24	18,0	6,10
240	1	0,75	20	15,0	6,65
260	1	0,75	18	13,5	7,20
280	1	0,75	16	12,0	7,75
300	1	0,75	16	12,0	8,30

(1) In addition to the default pallet, there is also a "jumbo" pack, composed of 2x2 pallets.

Store the insulation boards on a flat surface, keep dry and protected from sunlight.

### Characteristics

Thermal conductivity (W/(m.K)) (EN 12667)	30 - 60 mm 70 - 200 mm 210 - 300 mm	0,033 0,035 0,036
Length (mm) (EN 822)		1250 ± 8
Width (mm) (EN 822)		600 ± 8
Density (kg/m <sup>3</sup> )		30-35
Edge profile		rebate edge
Surface		smooth
Compressive strength at 10% deformation (kPa) (EN 826)		CS(10\Y)300
Dimensional stability (EN 1604)		DS(70,90)
Long term water absorption by immersion (%) (EN 12087)		WL(T)0,7
Reaction to fire (Euroclass)		E
Water vapour permeability (μ) (EN 12086)		150
Tensile strength perpendicular to faces (kPa) (EN 1607)		TR200
Compressive creep (EN 1606)	60 - 120 mm 130 - 300 mm	CC(2/1,5/50)130 NPD

NPD = no performance determined

### Installation

Use a suitable adhesive for adhesion to underground walls.

Always consult the local regulations and contact the manufacturer for technical questions.

After installation the insulation boards must be protected against weather conditions and sunlight.

**SOPREMA** reserves the right to amend the composition of its material and consequently their prices, without prior notice. For this reason, all orders will be accepted only in accordance with the conditions and technical specifications in force at the date of order.

Contact: [www.soprema.com](http://www.soprema.com)

## Certifications

---

ATG H892 (B)

ATG 3135 (B)

KOMO K98585 (NL)

KOMO K98586 (NL)

KOMO K98587 (NL)

KOMO K98588 (NL)

See certificates for more information.

## Special indications

---

### Hygiene, Health and Environment

The product does not contain any substance which is likely to be detrimental to your health or to the environment and complies with generally admitted Health and Safety Requirements.

### Quality-, Environment- and Safety Management

**SOPREMA** always recognises as a high level of importance the quality of the products, the environment and safety.

For this reason, we operate independently monitored Quality and Environment Assurance Systems in line with

**EN ISO 9001** and **EN ISO 14001**.