

FLAGON FLEXOCOL W LV

Description

FLAGON FLEXOCOL W LV is a ready-to-use, single component, moisture curing polyurethane adhesive.

It is used on flat roof applications to bond fleece-backed PVC and TPO waterproofing membranes to glassfleece faced insulation boards.

Under the influence of the humidity in the air, adhesion will take place.

Characteristics

Composition	polyurethane resins
Open time ⁽¹⁾	±30 min. (20 °C)
Curing time ⁽¹⁾	±90 min. (20 °C)
Consumption	±100 m ² / 20 l
Application temperature	+5 / +30 °C

⁽¹⁾ Depending on conditions (temperature, relative humidity, ...)

Packing & storage

Polybottle 20 l

Minimum 6 months in original unopened packaging, stored in a dry and cool place at a temperature between +5 and +30 °C.

Installation

The substrate must be clean, solid and free from dust and grease.

Use a lambs-wool roller to apply the adhesive on the substrate.

Wait 10 minutes, to allow the solvent to evaporate, and roll the membrane onto the coated substrate.

Prevent air entrapments.

Cleaning tools:

- remove uncured product with FLAGON Solvent 6 or FLAGON Solvent 13
- cured product needs to be removed mechanically

Special indications

Hygiene, Health and Environment

For more information, please refer to the relevant safety data sheet.

Quality-, Environment- and Safety Management

SOPREMA always recognises as a high level of importance the quality of the products, the environment and safety.

For this reason, we operate independently monitored Quality and Environment Assurance Systems in line with

EN ISO 9001 and **EN ISO 14001**.