

## FLAGON SV Copper Art

### Description

Membrane composed of flexible PVC and a fiberglass reinforcement.  
The upper surface is copper coloured.  
Used for detailing work in combination with Copper Art PVC membranes.  
The membrane is distinguished by a very high resistance to weathering, UV-rays and with a high resistance to puncture.

### Composition

|                   |              |
|-------------------|--------------|
| Material          | flexible PVC |
| Reinforcement     | fiberglass   |
| Colour upper side | copper       |

### Packing

|                         |      |
|-------------------------|------|
| Membrane thickness (mm) | 1,5  |
| Length of the roll (m)  | 20   |
| Width of the roll (m)   | 1,60 |
| Mass of the roll (kg)   | 57,6 |
| Rolls/pallet            | 12   |

### Characteristics

|                                                               |     |                             |
|---------------------------------------------------------------|-----|-----------------------------|
| Membrane thickness (mm) (EN 1849-2)                           | MDV | 1,5                         |
| Mass (kg/m <sup>2</sup> ) (EN 1849-2)                         | MDV | 1,80                        |
| Maximum tensile force (N/mm <sup>2</sup> ) (EN 12311-2 met B) | MLV | 9                           |
| Elongation at maximum tensile force (%) (EN 12311-2 met B)    | MLV | 200                         |
| Resistance to tear (nail shank) (N) (EN 12310-2)              | MLV | 135                         |
| Foldability at low temperature (°C) (EN 495-5)                | MLV | -25                         |
| Peel resistance joint (N/50 mm) (EN 12316-2)                  | MLV | 200                         |
| Shear resistance joint (N/50 mm) (EN 12317-2)                 | MLV | 540 (rupture outside joint) |
| Watertightness (EN 1928 met B)                                |     | conform                     |
| Dimensional stability (%) (EN 1107-2)                         | MLV | 0,1                         |
| Durability: exposure to UV, heat and water (EN 1297)          |     | grade 0                     |
| Resistance to root penetration (EN 13948)                     |     | pass                        |
| Resistance to static loading (kg) (EN 12730 met A)            | MLV | 20                          |
| Reaction to fire (EN 11925-2 / EN 13501-1)                    |     | E                           |

MDV = manufacturer declared value / MLV = manufacturer limiting value / NPD = no performance determined

### Installation

Adhered applied for detailing work in combination with Copper Art PVC membranes.  
The overlaps need to be welded with hot air.  
The membrane is applied in conjunction with accessories from Flag.

### Certifications

- ATG 2817 (B)
- CTG 604 (NL)
- BBA 97-3430 (UK)
- See certificates for more information.

### Special indications

#### Hygiene, Health and Environment

The product does not contain any substance which is likely to be detrimental to your health or to the environment and complies with generally admitted Health and Safety Requirements.  
For more information, please refer to the relevant safety data sheet.

#### Quality-, Environment- and Safety Management

**SOPREMA** always recognises as a high level of importance the quality of the products, the environment and safety.  
For this reason, we operate independently monitored Quality and Environment Assurance Systems in line with **EN ISO 9001** and **EN ISO 14001**.

**SOPREMA** reserves the right to amend the composition of its material and consequently their prices, without prior notice. For this reason, all orders will be accepted only in accordance with the conditions and technical specifications in force at the date of order.

Contact: [www.Soprema.com](http://www.Soprema.com)