

VENTIROCK SBS 3 TF

Description

Membrane with a vapour-pressure and tension dispersion system, composed of elastomer modified bitumen and a composite polyester reinforcement.

Used as a base layer within a multi layer waterproofing system on surfaces where partial adhesion is required.

The upper surface is finished with talcum/sand.

The lower surface is provided with thermofusible bitumen stripes alternated with non-stick stripes protected by a thermofusible film.

Composition

Reinforcement	composite polyester
Finish upper side	talcum/sand
Finish lower side	thermofusible film
Coating mass	elastomer modified bitumen

Packing

Dimensions of the roll (m)	10 x 1
Mass/roll (kg)	41
Rolls/pallet	23

Characteristics

Membrane thickness (mm) (EN 1849-1)	MDV	3,0
Membrane mass (kg) (EN 1849-1) (indicative)	MDV	4,1
Tensile force L (N/5cm) (EN 12311-1)	MDV	440
Tensile force T (N/5cm) (EN 12311-1)	MDV	440
Elongation at maximum tensile force L (%) (EN 12311-1)	MDV	35
Elongation at maximum tensile force T (%) (EN 12311-1)	MDV	35
Dimensional stability (%) (EN 1107-1)	MLV	0,6
Resistance to tearing (nail shank) L (N) (EN 12310-1)	MDV	100
Resistance to tearing (nail shank) B (N) (EN 12310-1)	MDV	100
Flexibility at low temperature (°C) (EN 1109)	MLV	-15
Flow resistance at elevated temperature (°C) (EN 1110)	MLV	100

MDV = manufacturer declared value / MLV = manufacturer limiting value / NPD = no performance determined

Installation

- Torched with moderate flame to create adhesion of the thermofusible bitumen strips. The overlaps are torched.

Certifications



Special indications

Hygiene, Health and Environment

The product does not contain any substance which is likely to be detrimental to your health or to the environment and complies with generally admitted Health and Safety Requirements.

For more information, please refer to the relevant safety data sheet.

Quality-, Environment- and Safety Management

SOPREMA always recognises as a high level of importance the quality of the products, the environment and safety.

For this reason, we operate independently monitored Quality and Environment Assurance Systems in line with

EN ISO 9001 and **EN ISO 14001**.

SOPREMA reserves the right to amend the composition of its material and consequently their prices, without prior notice. For this reason, all orders will be accepted only in accordance with the conditions and technical specifications in force at the date of order.

Contact: www.Soprema.com