

SOPRABASE SLV 200 SF

Membrane composed of SBS modified bitumen with a fibreglass reinforcement. The upper surface is finished with sand/talcum. The lower surface is protected by a thermofusible film.

Application

Used as an underlayer in a multi-layer system or as a vapour control layer.

Composition

	SOPRABASE SLV 200 SF
Reinforcement	fibreglass
Upperside	talcum/sand
Lowerside	foil
Coating mass	SBS modified bitumen

Packing

	SOPRABASE SLV 200 SF
Dimensions of the roll (m)	16 x 1
Weight of the roll (kg)	46,5
Number of rolls per pallet	30

Characteristics

		SOPRABASE SLV 200 SF
Membrane thickness (mm)	MDV	2,0
Tensile strength: L (N/5cm) (EN 12311-1)	MDV	350
Tensile strength: T (N/5cm) (EN 12311-1)	MDV	200
Elongation at break: L (%) (EN 12311-1)	MDV	NPD
Elongation at break: T (%) (EN 12311-1)	MDV	NPD
Dimensional stability (%) (EN 1107-1)	MLV	NPD
Nail tear resistance: L (N) (EN 12310-1)	MLV	NPD
Nail tear resistance: T (N) (EN 12310-1)	MLV	NPD
Cold flexibility (°C) (EN 1109)	MLV	-20
Softening point (°C) (EN 1110)	MLV	110
Reaction to fire (EN 13501-1)		NPD
Water vapour transmission (m) (EN 12524)	MDV	150

MDV = manufacturer declared value / MLV = manufacturer limited value / NPD = no performance determined



TECHNICAL DATASHEET



BETF-223/071-14-eng
cancels and replaces
BETF-223/253-13-eng

Installation

Torch applied including the seldedge.

Certifications

CE 0749-CPD-BC2-310-0300-0123-01

Year : 2006
Standard : EN 13707, EN 13970
DOP : WPBBE223

Special indications

Health and Environment :

The membrane does not contain any substance which is likely to be detrimental to health or to environment and complies with generally admitted Health and Safety Requirements. For more detailed information, please refer to the relevant safety data sheet.

Quality control :

SOPREMA has always attached the highest importance to Quality Control. For this reason, we operate an independently monitored Quality Assurance System in line with **EN ISO 9001:2008** and **EN ISO 14001:2004**.



ISO 9001
ISO 14001

Marnix DERKS
Technical Director

SOPREMA UK Limited reserves the right to amend the composition of its material and consequently their prices, without prior notice. For this reason, all orders will be accepted only in accordance with **the conditions and technical specifications in force at the date of order.**

Tel. : 08451 948 727 - Fax. : 08451 948 728
www.soprema.co.uk - E-mail : info@soprema.co.uk

SOPREMA
GROUP