

SOPRAVAP EVA 35

Description

Membrane composed of SBS modified bitumen and a composite aluminium + fiberglass reinforcement. Used as a vapour control layer for buildings with high moisture production. The upper surface is finished with talcum/sand. The lower surface is protected by a thermofusible film.

Composition

	SOPRAVAP EVA 35
Reinforcement	composite aluminium + fiberglass
Finish upper side	talcum/sand
Finish lower side	thermofusible film
Coating mass	SBS modified bitumen

Packing

	SOPRAVAP EVA 35
Dimensions of the roll (m)	6 x 1
Mass of the roll (kg)	30
Number of rolls per pallet	30

Characteristics

		SOPRAVAP EVA 35
Membrane thickness (mm) (EN 1849-1)	MDV	3,5
Membrane mass (kg) (EN 1849-1) (indicative)	MDV	4,8
Tensile force L (N/5cm) (EN 12311-1)	MLV	550
Tensile force T (N/5cm) (EN 12311-1)	MLV	400
Elongation at maximum tensile force L (%) (EN 12311-1)	MLV	2,5
Elongation at maximum tensile force T (%) (EN 12311-1)	MLV	2,5
Resistance to tearing (nail shank) L (N) (EN 12310-1)	MDV	NPD
Resistance to tearing (nail shank) T (N) (EN 12310-1)	MDV	NPD
Flexibility at low temperature (°C) (EN 1109)	MLV	-20
Flow resistance at elevated temperature (°C) (EN 1110)	MLV	80
Water vapour diffusion-equivalent (m) (EN 1931)	MLV	1500

MDV = manufacturer's declared value / MLV = manufacturer's limiting value / NPD = no performance determined



SOPREMA

Bituminous waterproofing

TECHNICAL DATASHEET



BETF-WPBDE0230.c/EN
cancels and replaces
BETF-WPBDE0230.b/EN

Installation

- Torch-on or hot-air method including the overlaps.

Certifications



No.: /
Standard: **EN 13970**
Year: **2005**

Special indications

Hygiene, Health and Environment

The membrane does not contain any substance which is likely to be detrimental to your health or to the environment and complies with generally admitted Health and Safety Requirements.
For more information, please refer to the relevant safety data sheet.

Quality-, Environment- and Safety Management

SOPREMA always recognises as a high level of importance the quality of the products, the environment and safety.

For this reason, we operate independently monitored Quality and Environment Assurance Systems in line with **EN ISO 9001** and **EN ISO 14001**.



Marnix DERKS
Technical Director
Grobendonk, 08/03/2018

SOPREMA reserves the right to amend the composition of its material and consequently their prices, without prior notice. For this reason, all orders will be accepted only in accordance with the conditions and technical specifications in force at the date of order.

Contact: www.Soprema.com

SOPREMA
GROUP