

ELASTOPHENE FLAM 40 AR

ELASTOPHENE FLAM 40 AR is a flexible SBS elastomeric bitumen waterproofing membrane with a glass fleece reinforcement.

The topside is protected by slate chippings and the underside is covered by a thermofusible film.

ELASTOPHENE FLAM 40 AR has an AENOR certificate and complies with LBM(SBS)-40/G-FV UNE 104242-1:1999.

User application

ELASTOPHENE FLAM 40 AR is used as finishing layer in all two-ply elastomeric bitumen waterproofing systems.

All the applications are described in Technical Approvals or **SOPREMA**'s Technical Guidelines in force.

Composition

	ELASTOPHENE FLAM 40 AR
Reinforcement	Glass fleece
Binder	Elastomeric bitumen : blend of selected bitumen and SBS* thermoplastic polymers
Weight	4 kg / m ² *
Thickness (indicative) MDV ⁽¹⁾ according to 13707 Minimum on overlap	3,2 mm (± 0,2 mm) 2,5 mm (± 0,2 mm)
Topside	Slate chippings
Underside	Thermofusible film
Overlap	≥ 80 mm
*According to UEAtc directives concerning the normalization of waterproof elastomeric SBS bitumen coverings	
⁽¹⁾ MDV = Manufacturer's Declared Value	

Packaging

	ELASTOPHENE FLAM 40 AR
Dimensions of the roll	10 m x 1 m
Weight of the roll	about 40 kg
Storage	Upright on pallet with plastic wrapping
Roll lengths are given with a tolerance of < 1 %. Width of roll is given with a tolerance of 1% (UEAtc). Rolls must be stored upright on flat ground. During storage, protect the rolls against moisture. In cold weather, we recommend that the rolls be kept at a minimum temperature of + 2°C (+ 36 °F) for at least 5 hours before installation.	

Installation

ELASTOPHENE FLAM 40 AR must be applied only by heat welding or torch-on techniques.

Hot bitumen must not be used in the bonding process.

Special indications

Hygiene, health and environment:

The product does not contain any substance likely to be detrimental to health or to environment and complies with generally admitted Health and Safety Requirements. For further information, please refer to relevant Safety Data Sheet.

Traceability:


Product traceability is ensured through a manufacturing code present on the packaging.

Quality control:

SOPREMA has always attached the highest importance to the quality of its products, to the respect of environment and men.

For this reason, we apply an integrated management of the Quality and Environment certified **ISO 9001** and **ISO 14001**.

CE marking

 1119
ELASTOPHENE FLAM 40 AR SOPREMA 14 rue de Saint-Nazaire – CS 60121 67025 STRASBOURG cedex 06 Construction Product Regulation (CPR) Declaration of Performance : DoP n° WPBEX212 Certificate of Factory Production Control : 1119-CPR-13132, 13133, 13134.
EN 13707 Membrane composed of modified elastomeric bitumen and glass fleece reinforcement. Topside is covered with slate chippings and the underside is covered by a thermofusible film. Dimensions 10 m x 1 m x 3,2 mm (4 kg/m ²). Finishing layer, cannot be used as single layer application. Must not be applied with hot bitumen.

Essential characteristics	Performances	Harmonised Technical Specification
Classification for external fire exposure (Note 1)	F_{ROOF} (t1,t2,t3,t4)	EN 13707:2004 + A2:2009
Reaction to fire	E	
Watertightness	Conform	
Tensile properties : Tensile strength L x T (N / 50 mm) Elongation L x T (%)	≥ 250 x 150 2 x 2	
Root resistance	NPD	
Resistance to static loading (kg)	5	
Resistance to impact (mm)	400	
Resistance to tearing (N)	≥ 50	
Joint strength Peel resistance of joints (N / 50 mm) Shear resistance of joints (N / 50 mm)	NPD NPD	
Durability Flow resistance at elevated temperature after ageing	90°C	
Flexibility at low temperature	-16°C	
Dangerous substances (Notes 2 and 3)	Complies	

Note 1 : Since external fire performance depends on the other components of the roof build-up, no performance can be given.

Note 2 : This product does not contain asbestos or tar constituents.

Note 3 : Since there is no European test method available, no performance declaration for leaching behavior can be made. It must be made according to national rules in force in the place of use.

Additional characteristics	ELASTOPHENE FLAM 40 AR
	MLV*
Flow resistance at elevated temperature (EN 1110)	100 °C
Dimensional stability (EN 1107-1)	0,1 %
*MLV = Manufacturer's Limiting Value: Minimum value as started by the manufacturer to be met during testing of type, internal quality control or external supervision with a confidence level of 95 %	