

## TECHNICAL DATASHEET



# FLAGON EP/PR-F

### **Description**

Membrane composed of modified polyolefin (TPO) and a polyester reinforcement coupled on the back (except the overlap) with a fleece.

Used as single layer waterproofing.

The membrane is distinguished by a very high resistance to weathering and UV-ray and with a high resistance to puncture.

#### **Characteristics**

Composition	Standard	Unit	Value				Tolerance
Material	modified polyolefin (TPO)						
Reinforcement	polyester						
Finish lower side				flee	ece		
<b>Technical characteristics</b>							
Membrane thickness	EN 1849-2	mm	1,2	1,5	1,8	2,0	± 5 %
Mass	EN 1849-2	kg/m²	1,35	1,60	1,88	2,05	
Tensile force (L / T)	EN 12311-2	N/50 mm	≥ 1100				
Elongation at maximum tensile force (L / T)	EN 12311-2	%	≥ 15			11.7	
Tear resistance (L / T)	EN 12310-2	N	≥ 300				
Resistance to impact	EN 12691-A	mm	≥ 450	≥ 800	≥ 900	≥ 1250	
Foldability at low temperature	EN 495-5	°C	≤ -40			6.7.7	
Peel resistance joint	EN 12316-2	N/50 mm	≥ 200				
Shear resistance joint	EN 12317-2	N/50 mm	≥ 600 rupture outside joint				
Watertightness	EN 1928		pass				
Dimensional stability	EN 1107-2	%	≤ 0,5				
Durability: exposure to UV, heat and water	EN 1297		grade 0				
Resistance to root penetration	EN 13948		conform				
Resistance to static loading	EN 12730-B	kg		≥ 20			
Reaction to fire	EN 11925-2 / EN 13501-1			E			
Water vapour diffusion resistance coefficient $(\mu)$	EN 1931			150000			± 30 %
Packing							
Length of the roll	EN 1848-2	m	≥ 25	≥ 20	≥ 20	≥ 20	
Width of the roll	EN 1848-2	m		≥ 1,05 / 2,10			
Mass/roll		kg	± 35 / 71	± 34 / 67	± 39 / 79	± 43 / 86	
Rolls/pallet			46 /23	46 / 23	36 /18	36 /18	

#### **Installation**

Mechanically applied waterproofing.

The fleece can serve as an integrated separation layer.

The overlaps need to be welded with hot air.

The membrane is applied in conjunction with accessories from Flag.

in accordance with the conditions and technical specifications in force at the date of order.

#### **Certifications**

- BBA 00/3750 (1,2 - 1,5 mm) (UK)

- Systems with this product (1,2 mm) as waterproofing can meet classification Broof (t4) according to EN 13501 part 5.

See certificate for more information.

SOPREMA



SOPREMA reserves the right to amend the composition of its material and consequently their prices, without prior notice. For this reason, all orders will be accepted only



# **TECHNICAL DATASHEET**



## **Special indications**

#### Hygiene, Health and Environment

The product does not contain any substance which is likely to be detrimental to your health or to the environment and complies with generally admitted Health and Safety Requirements. For more information, please refer to the relevant safety data sheet.

#### **Quality-, Environment- and Safety Management**

**SOPREMA** always recognises as a high level of importance the quality of the products, the environment and safety. For this reason, we operate independently monitored Quality and Environment Assurance Systems in line with **EN ISO 9001** and **EN ISO 14001**.



TDS-NE-WPSIT0029.b/EN

