

PLASTIGUM 3 VV TF

Description

Membrane composed of plastomer modified bitumen and a fiberglass reinforcement.
Used as a base layer within a multi layer waterproofing system.
The upper surface is finished with talcum/sand.
The lower surface is protected by a thermofusible film.

Characteristics

| Composition | Standard | Unit | Value | Tolerance |
|--|------------|-------------------|----------------------------|-----------|
| Reinforcement | | | fiberglass | |
| Finish upper side | | | talcum/sand | |
| Finish lower side | | | thermofusible film | |
| Coating mass | | | plastomer modified bitumen | |
| Technical characteristics | | | | |
| Thickness | EN 1849-1 | mm | 2,1 | ± 5 % |
| Mass (indicative) | EN 1849-1 | kg/m ² | 3,0 | |
| Tensile force (L / T) | EN 12311-1 | N/50 mm | 350 / 200 | ± 20 % |
| Elongation at max. tensile force (L / T) | EN 12311-1 | % | NPD | |
| Dimensional stability | EN 1107-1 | % | NPD | |
| Resistance to tearing (nail shank) (L / T) | EN 12310-1 | N | NPD | |
| Flexibility at low temperature | EN 1109 | °C | ≤ 0 | |
| Flow resistance at elevated temperature | EN 1110 | °C | ≥ 130 | |
| Reaction to fire | EN 13501-1 | Class | E | |
| Water vapour diffusion-equivalent | EN 1931 | m | 40 | ± 20 % |
| Packing | | | | |
| Dimensions of the roll | EN 1848-1 | m | ≥ 10 x 1 | |
| Mass/roll | | kg | ± 30 | |
| Rolls/pallet | | | 25 | |

NPD = no performance determined

Installation

- Fully applied by torch-on or hot-air method including the overlaps.
- Loose-laid in a system with heavy surface protection, overlaps torched.

Special indications

Hygiene, Health and Environment

The product does not contain any substance which is likely to be detrimental to your health or to the environment and complies with generally admitted Health and Safety Requirements.
For more information, please refer to the relevant safety data sheet.

Quality-, Environment- and Safety Management

SOPREMA always recognises as a high level of importance the quality of the products, the environment and safety. For this reason, we operate independently monitored Quality and Environment Assurance Systems in line with **EN ISO 9001** and **EN ISO 14001**.

SOPREMA reserves the right to amend the composition of its material and consequently their prices, without prior notice. For this reason, all orders will be accepted only in accordance with the conditions and technical specifications in force at the date of order.

Contact: www.soprema.com