

SOPRAMASTIC 200

Description

Flexible mastic based on bitumen and synthetic rubber.
Used for sealing small tears, cracks, joints and for local repairs.

Characteristics

Composition	bitumen and synthetic rubber
Temperature resistance	-20 / +80 °C
Application temperature	+5 / +35 °C
Consumption	15-20 m/cartridge

Packing & storage

cartridge of 310 ml

Minimum 24 months in original unopened packaging, stored in a dry and cool place at a temperature between +5 and +20 °C.

Installation

SOPRAMASTIC 200 is applied with a gun on a clean and dust-free support.
It has excellent adhesion to most materials without prior treatment with a primer.
It can be applied on a slightly damp surface.

Cleaning tools:

White Spirit

Special indications

Hygiene, Health and Environment

For more information, please refer to the relevant safety data sheet.

Quality-, Environment- and Safety Management

SOPREMA always recognises as a high level of importance the quality of the products, the environment and safety.
For this reason, we operate independently monitored Quality and Environment Assurance Systems in line with **EN ISO 9001** and **EN ISO 14001**.